

EcoPlot Dryapply ASLAN PP 112



Matt, PVC free self-adhesive film in black and white for short to medium term applications

EcoPlot ASLAN PP 112 is a self-adhesive film in black and white for plotter-cut letterings and logos. It is PVC free and therefore an ecological and dimensional stable solution for short- to medium-term designs on flat surfaces, e.g. glass surfaces, walls, signs and construction of exhibition booths.

The film is ideal for plotter-cut designs. The unique ASLAN Dryapply technology guarantees an exceptionally clean, fast and easy dry application. Bubbles can be removed with ease thanks to very fine air release channels. In particular large sections can be applied much more easily.

For further information or questions regarding special applications please contact our technical advisory service: **+49 2204.708-80**

Construction

Face film:	PP	
Thickness:	~ 80 µm (3.15 mil)	
Adhesive:	Polyacrylate adhesive	square quantity: ~ 25 g/m ²
Release liner:	double sided PE coated paper, embossed	square weight: ~ 140 g/m ²

Characteristics

Adhesive strength (ASTM D903):	immediately: after 1 week:	immediately: ~ 9 N/25 mm after 1 week: ~ 15 N/25 mm
Dimensional stability:	applied onto aluminium after 48 hours stored at 70 °C (158 °F) (25 x 25 cm)	No shrinkage measurable
Chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum-based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
Light proofness:	DIN 53 388	non-fade grade: 6-8 (wool-scale)
Temperature:	application temperature: service temperature range:	min 15 °C (59 °F) -30 °C (-22 °F) up to +80 °C (176 °F)
Durability:	Up to 2 years outdoors, with vertical exposure, in central European standard climatic conditions.	

EcoPlot Dryapply ASLAN PP 112



Processing

Application

The film is to be applied dry only.

Using a squeegee, the material is to be applied with even and firm pressure, so that the adhesive can completely reach its final adhesion. Otherwise, a detachment of the self-adhesive film from the substrate might be caused.

For the application of letterings etc. we recommend our ASLAN application tapes or our mounting film ASLAN TMO. After removing the application tape, we additionally recommend to firmly press down the edges of the film once more with a squeegee.

It must always be ensured that no water accumulates at the cutting edges of the film (e.g. in metal or plastic frameworks) and no condensation forms on glass panes onto which the films has been installed. In such cases, and when the film is applied on a freestanding glass surface, a whitening of the adhesive might occur.

Storage:

Before application the films can be stored up to 2 years from date of production. The film must be stored at room temperature (15-25 °C / 59-77 °F) and at a relative air humidity of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either standing vertically or in a purposely designed 'hanging' racks.

State 07|2024

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.